

ARTICLE COMPRISING AN OXIDE LAYER ON A GaAs-BASED
SEMICONDUCTOR STRUCTURE AND METHOD
OF FORMING SAME

5

Abstract

A compound semiconductor structure is provided, which includes a GaAs-based supporting semiconductor structure having a surface on which a dielectric material is to be formed. A first layer of gallium oxide is located on the surface of the supporting semiconductor structure to form an interface therewith. A second layer of a Ga-Gd oxide is disposed on the first layer. The GaAs-based supporting semiconductor structure may be a GaAs-based heterostructure such as an at least partially completed semiconductor device (e.g., a metal-oxide field effect transistor, a heterojunction bipolar transistor, or a semiconductor laser). . In this manner a dielectric layer structure is provided which has both a low defect density at the oxide-GaAs interface and a low oxide leakage current density because the dielectric structure is formed from a layer of Ga_2O_3 followed by a layer of Ga-Gd-oxide. The Ga_2O_3 layer is used to form a high quality interface with the GaAs-based supporting semiconductor structure while the Ga-Gd-oxide provides a low oxide leakage current density.

20